
Product Name:	Graphite Filled Skydrol Resistant Dry Film Lubricant
----------------------	--

Product Number:	IP9136-R3
------------------------	-----------

Product Description:	<p>Spray applied, stoving cured, silicon resin modified dry film lubricant for use where high operating temperatures preclude the use of conventional oils and greases.</p>
-----------------------------	---

Suitable for application to steel, aluminium, magnesium and titanium alloys.

Used on, for example spherical bearing surfaces to protect against frottage corrosion and on bolts for torque and gives an exceptionally good rubbing wear resistance.

When used on bolts, it increases torque end loads. It is also used on turbine blade roots and fir trees where it reduces the likelihood of the disc splitting.

Approvals/Specifications:	<ul style="list-style-type: none">- MSRR 9276- OMat 4 / 44C- CPW 27- Alternative to the no longer made - PL239 (3862X9010) AFS473, which superseded PL 94 in about 1984
----------------------------------	--

Performance:	<p>Resistant to dry heat up to 400°C (750°F) in oxidizing atmospheres and 500°C (930°F) where oxygen is excluded, ester lubricants, Skydrol and corrosion.</p>
---------------------	--

Tri-n-Butyl-Phosphate: 3 hours @ 70°C

Dry Heat: 1000 hours at 400°C

Components:

Single Part Product. May be thinned for application using either IP985-Reducer or IP9151 Thinner.

IP985-REDUCER is preferred. IP9151 is still approved for use but is no longer a preferred solvent as it triggers risk phrase R40. Other solvents may be suitable in certain circumstances

Application:

Surface Preparation:

Ensure that surfaces are clean and free from dirt

Paint Preparation:

Stir well before use. All separated material must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use.

Application Method:

Spray a light coat and allow to dry for 10 - 20 minutes @ room temperature, 15-30°C, stove for 2 – 2.5 hours at 190 +/- 8°C (375°F). Where spraying is not possible small areas may be coated by brush.

Part cure procedure – where components require coating on multiple faces and/or multiple masking procedures, IP9136-R3 may be part cured to allow handling.

For this process a baking schedule of 30-40 minutes @ 150 +/- 8°C may be used.

The low bake allows parts to be handleable only. Full curing of the coating is only achieved after the full baking cycle.

Refer to RPS 661 / 10 for additional client specific details.

Drying Curing:

Air Dry for 10-20 minutes @ room temperature, 15-30°C, then stove for 2 – 2.5 hours at 190 +/- 8°C (375°F)

Technical Properties:

Supply Viscosity:	Ready for use
Flash Point:	27°C
VOC Content:	N / A
Colour:	Grey
Pack Size:	1 & 5 Litres
Density:	1.03 kg / litre
Gloss:	N / A
Thinner:	IP985-REDUCER is preferred. IP9151 is still approved for use but is no longer a preferred solvent as it triggers risk phrase R40. Other solvents may be suitable in certain circumstances
Solvent/Clean Up:	40006 Gun Clean
Catalyst:	Ready for use
Theoretical Coverage:	13.5 sq m/litre @ 25 micron

Storage:

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk