
Product Name:

Incralac Protective Lacquer for Non Ferrous Metals;
Brass & Copper

Product Number:

- 40005 – Gloss
 - 40058 – Satin
 - 40057 – Matt
-

Product Description:

Air drying clear lacquer initially developed for stringent military standards for use in protecting non-ferrous metals in arduous conditions.

This product is now available to the general market for protecting such metals as brass, aluminium and copper. With an excellent balance of hardness, adhesion and film toughness. Incralac has excellent resistance to UV light and resists yellowing and loss of gloss and clarity upon ageing. Originally developed for protection of brass shell cases, this product is intended for interior or exterior use.

Approvals/Specifications:

- NSN 8010-99-220-5827
-

Performance:

- Excellent salt spray performance
 - Gives good exterior weathering
-

Components:

Single Pack Product. May be thinned for application using 18802

Application:**Surface Preparation:**

Before application ensure removal of all polishing compounds and other surface contaminants by cleaning with cellulose thinners.

Paint Preparation:

Stir well before use. All separated material must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use.

Application Method:

Can be applied by Brush or Spray. Do not use below 10°C.

Apply 3-4 coats of Incralac. Each coat will deposit 6-10 microns of coating. Allowing to touch dry for 15 minutes between coats. After use clean equipment with cellulose thinners. Take care not to brush out the lacquer too heavily when applying the follow on coats, as it is possible to soften the previously applied coats.

Drying Curing:

Air Dry: 10 minutes

Hard Dry: 1 hour

Technical Properties:

| | |
|--------------------------|--|
| Supply Viscosity: | 50 Secs / ISO3 Cup / 23±2°C |
| Flash Point: | >0°C<21°C |
| VOC Content: | 768 gms / litre |
| Colour: | Clear |
| Pack Size: | 5 litre |
| Density: | 0.91 kg/litre |
| Gloss: | 40005 – Gloss 40058 – Satin (40±5% on 60°head) 40057 – Matt (10±3% on 60°head) |

Technical Data Sheet



| | |
|------------------------------|---------------------------------------|
| Thinner: | 18802 |
| Solvent/Clean Up: | 18802 |
| Catalyst: | N / A |
| Theoretical Coverage: | 6 sq m/litre @ 20 microns (3-4 coats) |

Storage:

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk