
Product Name:

Air Drying Cellulose Finish

Product Number:

- 30000 – Range
 - 30000 – Clear high build
 - 30002 - Matt Black (< 5% gloss)
 - 30004 - Gloss Dark Green
 - 30006 - Black Self Revealing Lacquer
 - 30010 - Satin Saddle Brown
 - 30011 - Semi-Matt Black (20% gloss)
 - 30014 - Gloss Brown
 - 30015 - Gloss Clear High Surface Slip
 - 30016 - Semi-Matt White
-

Product Description:

Cellulose Colour Coatings designed to provide a Rapid Drying protective finish.

- Ideal for use where rapid handling after coating is a requirement.
 - Suitable for Dip or Spray
 - Used as decorative finish on products where durability is not the prime factor and/or as a touch up system.
-

Approvals/Specifications:

N/A

Performance:

Rapid drying coatings for application onto a range of metallic and non-metallic substrates. The coating can be used as a protective finish on copper and brass components where finger print damage and tarnishing can be an issue for infrequently handled decorative applications.

Components:

Single Pack Product. May be thinned for application using 18802

Application:

Surface Preparation:	Surfaces must be clean and free from grease or polishing compounds.
Paint Preparation:	Single part product. Thin as required with 18802 thinner prior to application.
Application Method:	Spray application. Touch up areas may be brush applied.
Drying Curing:	Air drying coating. May be force dried at up to 80°C if required. Flash off - 10 minutes. Hard dry – 2 hours

Technical Properties:

Supply Viscosity:	70 – 80 seconds ISO5 @ 23+/- 2°C
Flash Point:	< 21°C closed cup method
VOC Content:	N/A
Colour:	Variant specific
Pack Size:	5 litre
Density:	0.95 – 0.99 kg/l
Gloss:	Variant specific
Thinner:	18802
Solvent/Clean Up:	40006 gun cleaner
Catalyst:	N/A
Theoretical Coverage:	10-12 sq m per litre

Storage:

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk