Technical Data Sheet



Product Name:	Rockhard Stoving Matt Black Epoxy Coating	
Product Number:	615-155-001	
Product Description:	Rockhard Stoving Matt Black has been developed to meet the latest requirements of the aerospace industry and multiple customer specifications. The coating is designed for use primarily on aero- engine, heat exchanger and helicopter gearbox components on a variety of substrates including magnesium / aluminimum / steel and titanium. The cured coating is a tough durable weather resistance finish that will withstand many hard environments and chemical resistance requirements.	
	Uses include non-reflective coatings on optical instruments, laser enclosures and miltary non-reflective applications.	
Approvals/Specifications:	 DTD 56D BAE P3507 (S26-350 nNow Airbus ABP 4-2131) MSRR 9226, OMat 7 / 174A, RR Code: 138435 NGPS 126, Type 2B Previous Reference: 444 / 80 Nato Stock No: 8010-99-225-3339 	
Performance:	 Meets the requirements of multiple specifications to include: Salt Spray: 1,000 hours at ASTM-B117 High Temperature: 1,000 hours @ 220°C Low Temperature Resistance: 24 hours @ -50°C Hydraulic Fluid (Skydrol) Resistance: 168 hours @ 70°C followed by 1,500 grams scratch Aerospace Fuel Resistance: 48 hours @ 40±2°C 	
Components:	Single Pack Product. May be thinned for application using 665-550- 025	

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995

Technical Data Sheet



Application:

Surface Preparation:	Substrate must be clean, dry and grease free. Bare metal adhesion is improved through abrasion or grit blasting. To be applied over 700-155-003 chromate or IP985-6500 Rockhard non-chromate primers.	
Paint Preparation:	Single Pack range of products – may be applied at supply viscosity. Thinning with up to 20% IP-Reducer may be required upon application.	
Application Method:	Apply by spray; conventional or HVLP. For full details refer to Indestructible Application Guide IPAS-21.	
Drying Curing:	Air Dry: 15 minutes Part Bake between coats: 150±10°C for 30-60 minutes Full Cure (standard): 190±5°C for 60-90 minutes Care must be taken to comply with end user requirements where customer approval to an alternative baking schedule has been agreed.	
Technical Properties:		Clear, 18-24 secs ISO5 @ 23±2°C
Technical Properties:	agreed.	Clear, 18-24 secs ISO5 @
Technical Properties:	agreed. Supply Viscosity:	Clear, 18-24 secs ISO5 @ 23±2°C
Technical Properties:	agreed. Supply Viscosity: Flash Point:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content: Colour:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre Black
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content: Colour: Pack Size:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre Black 1 and 5 Litres
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content: Colour: Pack Size: Density:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre Black 1 and 5 Litres 1.15kg / litre
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content: Colour: Pack Size: Density: Gloss:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre Black 1 and 5 Litres 1.15kg / litre Matt
Technical Properties:	agreed. Supply Viscosity: Flash Point: VOC Content: Colour: Pack Size: Density: Gloss: Thinner:	Clear, 18-24 secs ISO5 @ 23±2°C ≥21-≤32°C 559 g/litre Black 1 and 5 Litres 1.15kg / litre Matt 665-550-025

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995

Technical Data Sheet



Storage:	Highly flammable liquid: store and use in accordance with the flammable liquid regulations
	Shelf Life: 12 months temperate; 6 months tropical Before use, refer to Product Safety Data Sheet
Disclaimer:	The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.
Safety Data Sheets:	For Safety Data Sheets please contact our Sales Department: Tel: +44(0)121 702 2485
	Email: sales@indestructible.co.uk