Technical Data Sheet



Product Name:	Lead Free Stoving Ammunition Lacquer	
Product Number:	IP80-25 (09982)	
Product Description:	Lead free stoving ammunition lacquer for use on various ammunition components including naval shells missiles etc. For use by Triservice, Army, Navy and RAF. Previously known as CS 3100 B	
Approvals/Specifications:	 Was released to Def Stan 80-35, Issue 1, which was cancelled in June 2001. Nevertheless, we still test this product to the requirements of Def Stan 80-35 CS 3100 	
Performance:	Released to the requirments of Defence Standard 80-25	
Components:	Single component baking product. May be viscosity adjusted for application with 665-550-025 Thinner.	
Application:		
Surface Preparation:	Surfaces must be clean and grease free. Suitable for application over ferrous substrate primed with Def 80-123 primer. Non-ferrous substrate primed with Def 80-124. Under normal conditions a phosphate in accordance with Def 03-11 or a BS2X32 primer may be used.	
Paint Preparation:	Stir well before use.	
Application Method:	By spray over suitable pre-treatment. Normally 2 coats.	
Drying Curing:	Cure 1 hour at 140°C	

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995

Technical Data Sheet



Technical Properties:	Supply Viscosity:	45±5 seconds (ready to use)	
	Flash Point:	≥21°C & <32°C	
	VOC Content:	nominal 500 g/lt	
	Colour:	Clear	
	Pack Size:	5 Litres	
	Density:	1.1 – 1.3kg/l	
	Gloss:	Glossy	
	Thinner:	665-550-025	
	Solvent/Clean Up:	40006	
	Catalyst:	N/A	
	Theoretical Coverage:	16 sq / m per liter @ 25 microns	
Storage:	Highly flammable liquid: store and use in accordance with the flammable liquid regulations Shelf Life: 12 months temperate; 6 months tropical Before use, refer to Product Safety Data Sheet		
Disclaimer:	The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.		
Safety Data Sheets:	For Safety Data Sheets please contact our Sales Department:		
	Tel: +44(0)121 702 2485	Tel: +44(0)121 702 2485	
	Email: sales@indestructible.c	Email: sales@indestructible.co.uk	

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995