
Product Name:

Two Part Epoxy Anti-Corrosive Primer

Product Number:

IP9064-6500

Product Description:

Anti-corrosive non chromate primer; semi matt grey, used on its own, or as a base for use with either the IP 9064 or IP3 low VOC epoxy or IP6 polyurethane ranges.

Designed to be an alternative to IP9064-6362 Chromate Primer for use on Aerospace Applications. This primer provides a high level of corrosion protection for Non-Ferrous and Ferrous substrates.

Approvals/Specifications:

Complies with MSRR 9064; Def 80-161, supercedes DTD 5555; 5580;

Performance:

After 7 days air curing, or force cure 30 minutes at 80°C will pass;

- Heat resistance: 48 hours at 400°F (240°C)
 - Heat resistance: 100 hours at 180°C
 - Hot oil; 8 hours in ASTM Fluid 101 (ASTM D 471) at 350°F (176°C) showing no peeling or softening
 - Fuel resistance: ASTM ref fuel B 4 hours at room temperature without peeling or softening
 - Resistant to 10 cycles 4 hours at 150°C (300°F) 20 hours in salt water fog as part of system
 - Resistant to temperatures of down to at least -40°C
-

Application:**Surface Preparation:**

All substrate must be clean and grease free. Suitable for use over abraded or blasted surfaces. May be applied over chromate or non-chromate pre-treatment.

Paint Preparation:

Mix 2 parts IP9064-6500 to 1 part IP9064-CAT-M by volume.

Allow 15 minutes dwell time, and re-stir before use.

Pot life; not less than 4 hours at 60 – 80°F; 15 – 26°C

Technical Data Sheet



Application Method:	Apply by spray, conventional, HVLP or compliant guns are all suitable. Can be thinned with 5-10% IP9064-Thin if required.
Drying Curing:	Touch dry 45 minutes; Hard dry for overcoating: 16-24 hours at room temperature. Can be force cured: typical schedule: 30 minutes @ 125°C (257°F)

Technical Properties:

Supply Viscosity:	Supplied ready for use
Flash Point:	25°C
VOC Content:	504 g/lit
Colour:	Light Grey
Pack Size:	1 & 5 litre
Density:	1.35 g/ml part A, 0.87 g/ml part B
Gloss:	Matt Primer
Thinner:	IP9064-Thin
Solvent/Clean Up:	40006 gun cleaner
Catalyst:	IP9064-CAT
Theoretical Coverage:	12-14 sq m per litre

Storage:

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Technical Data Sheet



Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk