

IP9138-R1

Heat and Skydrol Resistant Air Drying Aluminium



Product Description

A heat resistant, air drying enamel for use with IP9139, PL101 and IP9029 heat resistant stoving enamel as a touch up. Resistant to ester lubricants, Skydrol, heat and corrosion. Additionally used as good colour match touch up for burnished Ipcote IP9183-R1 , IP9356 , and IP9442 . It also has many other uses in extreme environments and is applied, for example on aircraft wheels and under carriages in new manufacture and maintenance. It may also have application as a marking ink or paint in the aircraft industry, as it also adheres to polyurethane and epoxy, with resistance to skydrol brake fluid, the new replacements for Genklene, chemicals, heat etc.



Approvals/Specifications

MSRR9040, O/MAT 7/22B, V2500, CoMat 07-038, MTU – MTS 1254
 Alternative to NSN 8010-99-2204993, 9306965, replaces AFS 1567

Alternative to PL82, E3892, 1912-A-8000, Textron approval, Alternative to International Paints Number HTA154 - P6430 & SSP501/502
 Agusta Westland WHPS402, which contains both IP9189 and IP1938 for repair.



Performance

Performance data applies only after 24 hours, tests on steel include:

- 1000 Hours at 500°C (930°F) dry heat
- 100 Hours at room temperature in Ester lubricants
- 3 Hours at 70°C (160°F) in Skydrol
- 100 Hours continuous salt spray



Components

Single component product. May be thinned with 665-550-025 Thinner for application.



Application

Surface Preparation



Substrate must be clean and grease free as a minimum. May be applied over abraded, phosphate or chromated substrate.

Paint Preparation



Stir well before use. All separated material must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage

Application Method



temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use.

Intended for spray application. Small areas may be brushed. Aerosol version available; please consult our Sales Department

Drying Curing



Allow to air dry for a minimum of 1 hour before handling.



Technical Properties

Supply Viscosity	Supplied ready for use
Flash Point	25 – 27°C closed cup
VOC Content	330g/litre
Colour	Aluminium
Pack Size	1 and 5 litre
Density	1.03 kg/litre
Gloss	N/A
Thinner	665-550-025
Solvent/Clean Up	40006
Catalyst	N/A
Theoretical Coverage	23 sq/m per litre @ 25 microns dft



Storage

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages

Safety Data Sheets

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485 Email: sales@indestructible.co.uk