
Product Name:

High Heat Erosion Coating White MSRR9188

Product Number:

IP9188-R2

Product Description:

Latest generation of products developed with the environment in mind – Toluene Free.

IP9188-R2 is an erosion resistant stoving coating, resistant to heat, corrosion and aircraft fluids. Suitable for use on steel and aluminium components with a continuous running temperature of less than 280°C (535°F), for use on engine components operating up to 250°C.

This material is now only normally made in white as a standard product, although it can be made to BS381C-693 (Rolls Royce Grey) and BS381C-175 (Blue), and other colours including BS381C-631. Please specify the colour required when placing an order.

Current uses include impellers in gas compressors pumping North Sea gas from offshore platforms. Resistant to Hydrogen Sulphide and Carbon Dioxide which is used to protect rough casting against corrosion and crusting.

Approvals/Specifications:

- MSRR9188, OMat 7/5E
 - Alternative to SE164, PL250 and 3862-X-0000
 - Performs to DTD900 / 6002, MTU-MTS
-

Performance:

Routinely quality tested to meet the following parameters:

- 100 hours dry heat @ 300°C (575°F)
 - 100 hours ester lubricant @ 150°C (300°F)
 - 3 hours skydrol @ 70°C (160°F)
 - 100 hours engine fuel @ 150°C (300°F)
-

Components:

Single component baking product. May require thinner IP985-Reducer

Application:

| | |
|-----------------------------|---|
| Surface Preparation: | Substrate must be clean and grease free as a minimum. May be applied over abraded, phosphate or chromated substrate. |
| Paint Preparation: | Stir well before use. All separated material must be re-incorporated into the bulk product. No time limits are specified for the mixing operation. The operator must be satisfied that the product including any thinning solvent is thoroughly mixed before use. Where mechanical mixing is employed care must be taken to not heat the product to above the maximum storage temperature. Mixing in open containers should be limited to <10 minute periods to ensure that solvent evaporation does not compromise the product. Shaking or rolling in closed containers is an acceptable mixing method for small volume products supplied ready for use. |
| Application Method: | Designed for Spray application. Application procedure IPAS 016 |
| Drying Curing: | Spray one coat and flash off for 20 minutes, apply a second coat and flash off for 30 minutes. Then stove for 2 hours at 185-195°C (365-385°F). Repeat process if greater film thickness is required. |

Technical Properties:

| | |
|------------------------------|---------------------------|
| Supply Viscosity: | 45-55 s ISO 4 @ 23°C |
| Flash Point: | 24-26°C closed cup |
| VOC Content: | 537 g/litre |
| Colour: | White |
| Pack Size: | 1 and 5 litre |
| Density: | 1.23 kg/litre |
| Gloss: | Semi-Gloss |
| Thinner: | IP985-Reducer or IP9151 |
| Solvent/Clean Up: | 40006 Gun Cleaner |
| Catalyst: | N/A |
| Theoretical Coverage: | 16 sq m/litre @ 25 micron |

Storage:

Highly flammable liquid: store and use in accordance with the flammable liquid regulations

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk
