Technical Data Sheet



Product Name: 2 Part Low Temperature Curing Epoxy Sealant and

Adhesive

Product Number: NML35 Part A & B

Product Description: NML 35 is a non-flowing high strength and general bonding

adhesive.

Epoxy based 2 part product used in aero engine applications such

as bonding PTFE pads onto fan discs.

Approvals/Specifications - MSRR 9026

- AFS 525

- AFS 712

Performance: After curing, with a glue line 0.05mm – 0.15mm thick for 1 hour at

100°C, withstands double lap shear strength testing follows:

- Dry air at 80°C - 1,000 hours

- Hydraulic Fluid at Room Temperature – 1,000 hours

Synthetic Oil at Room Temperature – 1,000 hours

- Fuel at Room Temperature - 1,000 hours

- Distilled Water at Room Temperature – 1,000 hours

Components: Product: NML35A

Catalyst: NML35B

Catalyst: NML35F
Thinner: N/A

Application:

Surface Preparation: Ensure that all surfaces are clean and free from dirt

Paint Preparation: Mix 70:30 parts by weight - Part A to B

The two components shall be thoroughly mixed until homogeneous.

Application Method: Ask for RPS 407 / 4

Drying Curing: The mixed adhesive has a pot life of approximately ≤2 hours at

room temperature. Glue line shall be 0.05mm to 0.15mm and then cured for 1 hour at 100°C or 3 hours at 70°C or 24 hours at room

temperature.

Technical Data Sheet



Technical Properties:	Supply Viscosity:	N/A
-----------------------	-------------------	-----

Flash Point: >80°C

VOC Content: 0 g/lt

Colour: N/A resinous paste

Pack Size: Part-A: 700g, Part-B: 300g

Density: 1.14 g/ml mixed

Gloss: N/A

Thinner: N/A

Solvent/Clean Up: 40006 Gun Cleaner

Catalyst: Part A&B 2 part kit

Theoretical Coverage: 18 m²/kg @ 50 micron

Storage:

 $5-35^{\circ}\text{C}$ in suitable container. This material will burn if involved in a

fire.

Shelf Life: 12 months temperate; 6 months tropical

Before use, refer to Product Safety Data Sheet

Disclaimer:

The information printed in this publication is based upon the research and experience of Indestructible Paint Ltd. No representation of warranty is made, however, concerning the accuracy or completeness of the information presented in this publication. Indestructible Paint Ltd make no warranty or representation of any kind, express or implied. Including without information limitation any warranty or merchantability or fitness for any particular purpose, and no warranty or representation shall be implied by law or otherwise. Any products sold by Indestructible Paint Ltd are not warranted as suitable for any particular purpose to the buyer. The suitability of any products for any purpose in particular to the buyer is for the buyer to determine. Indestructible Paint Ltd assumes no responsibility for the selection of products suitable to the particular purpose of any particular buyer. Indestructible Paint Ltd shall in no event be liable for any special, incidental or consequential damages.

Safety Data Sheets:

For Safety Data Sheets please contact our Sales Department:

Tel: +44(0)121 702 2485

Email: sales@indestructible.co.uk