Technical Data Sheet



Product Name:	High Heat Resisting Protective Enamel Matt Black	
Product Number:	PL73	
Product Description:	A tough, high heat resistant coating, capable of withstanding 500°C (930°F). It is also resistant to a wide range of oils, lubricants and chemicals.	
Approvals/Specifications:	 MSRR 9306 OMat 7/148 RR Code 137525 MIL-C-81751MOD RP 899 	
Performance:	Tested for resistance to heat at up to 500°C (930°F) and to all major aerospace fluids including Skydrol.	
Components:	Single Pack Product.	
Application:		
Surface Preparation:	Surfaces must be clean, grease and oil free and clear of any prior coatings. Abrasive blast surface to be coated.	
Paint Preparation:	Shake/ stir well before use	
Application Method:	Spray using conventional gun or brush 2 coats to a degreased, abrasive blasted surface, with a 5 minute flash off between coats,	
Drying Curing:	Air dry for 30 minutes, then stove at 190°C (375°F) for 2 hours. Apply to RPS 661/28.	

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995

Technical Data Sheet



Technical Properties:	Supply Viscosity:	ISO 5 Cup 25 -30 seconds	
	Flash Point:	24°C/3/Paint UN1263	
	VOC Content:	24 0/3/1 and 011/203	
	Colour:	- Matt Black	
	Pack Size:		
		1 Litre containers	
	Density:	1.560 +/- 0.020kg/l	
	Gloss:	Matt	
	Thinner:	IP9151	
	Solvent/Clean Up:	IP9151	
	Catalyst:	N/A	
	Theoretical Coverage:	-	
Storage:	Highly flammable liquid: store flammable liquid regulations	Highly flammable liquid: store and use in accordance with the flammable liquid regulations	
	Shelf Life: 12 months temper	ate; 6 months tropical	
	Before use, refer to Product	Safety Data Sheet	
Disclaimer:			
	Indestructible Paint Ltd. No represer accuracy or completeness of the info Paint Ltd make no warranty or represe without information limitation any war purpose, and no warranty or represer products sold by Indestructible Paint purpose to the buyer. The suitability buyer is for the buyer to determine. I the selection of products suitable to the	ation is based upon the research and experience of tration of warranty is made, however, concerning the rmation presented in this publication. Indestructible entation of any kind, express or implied. Including ranty or merchantability or fitness for any particular nation shall be implied by law or otherwise. Any Ltd are not warranted as suitable for any particular of any products for any purpose in particular to the ndestructible Paint Ltd assumes no responsibility for ne particular purpose of any particular buyer. ent be liable for any special, incidental or	
	For Safety Data Sheets place	se contact our Sales Department:	
Safety Data Sheets:		be contact our bales Department.	
Safety Data Sheets:	Tel: +44(0)121 702 2485		

Indestructible Paint Ltd, 16-25 Pentos Drive, Sparkhill, Birmingham B11 3TA Tel: +44(0)121 702 2485, Fax: +44 (0)121 778 4338, E-Mail: <u>sales@indestructible.co.uk</u>, Web: <u>www.indestructible.co.uk</u> Registered in England: 1376995